

# ExxonMobil™ LDPE LD 202.48

## Low Density Polyethylene Resin

### Product Description

LD 202.48 is an LDPE extrusion coating grade, especially designed for high speed, lightweight extrusion coating applications providing: - high speed processability - good heat sealing properties LD 202.48 offers an excellent coating on non-woven substrates. Its high melt-index combined with low density gives this grade the right balance between : - Adhesion onto non-wovens - Flexibility after coating

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>Latin America</li> <li>North America</li> </ul>
Additive	<ul style="list-style-type: none"> <li>LD 202.48: Antiblock: No; Slip: No; Thermal Stabilizer: No</li> </ul>
Applications	<ul style="list-style-type: none"> <li>Coextrusion Coating</li> <li>Extrusion Coating</li> <li>Extrusion Lamination</li> <li>Document Plastification</li> <li>Food Packaging</li> <li>High Speed, Thin Weight Coatings</li> <li>Non-Woven Coating</li> <li>Thermal Lamination</li> </ul>
Form(s)	<ul style="list-style-type: none"> <li>Pellets</li> </ul>
Revision Date	<ul style="list-style-type: none"> <li>03/01/2010</li> </ul>

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.915 g/cm <sup>3</sup>	0.915 g/cm <sup>3</sup>	ASTM D1505
Melt Index (190°C/2.16 kg)	12 g/10 min	12 g/10 min	ASTM D1238
Peak Melting Temperature	219 °F	104 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	183 °F	84 °C	ASTM D1525

Coating Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Draw Down (Constant output at 35 rpm)	240 m/min	240 m/min	ExxonMobil Method
Neck-in			ExxonMobil Method
164 ft/min (50 m/min), Constant output at 35 rpm	1.6 in	4.1 cm	
328 ft/min (100 m/min), Constant output at 35 rpm	1.4 in	3.6 cm	

### Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

### Processing Statement

Typical values obtained on a pilot co-extrusion line at ExxonMobil Chemical Europe Technical Center at an air gap of 170 mm (6.7 in).

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

**ExxonMobil™ LDPE LD 202.48**  
Low Density Polyethylene Resin

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)