

ExxonMobil™ LDPE LD 637.LI

Low Density Polyethylene Resin

Product Description

ExxonMobil™ LD 637.LI is a high melt index LDPE homopolymer resin intended for injection molding or compounding applications requiring high flow. It is ideal for tamper-evident, tear-to-open closures. It can also be used in compounds and concentrates.

General

Availability ¹	- Latin America - North America
Additive	- Antiblock: No - Slip: 550 ppm - Thermal Stabilizer: No
Applications	- Caps - Closures - Compounding - Injection Molding - Masterbatch Base Resin - Viscosity Modifier
Form(s)	Pellets
Revision Date	06/17/2020

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.922 g/cm ³	0.922 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	40 g/10 min	40 g/10 min	ASTM D1238
Peak Melting Temperature	232 °F	111 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	183 °F	84.0 °C	ExxonMobil Method

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	1900 psi	13 MPa	ExxonMobil Method
Tensile Strength at Break	1300 psi	8.8 MPa	ExxonMobil Method
Elongation at Yield	40 %	40 %	ExxonMobil Method
Elongation at Break	72 %	72 %	ExxonMobil Method
Flexural Modulus - 1% Secant	39000 psi	270 MPa	ExxonMobil Method
Durometer Hardness			ExxonMobil Method
Shore A, 15 sec	90	90	
Shore D, 15 sec	47	47	

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Instrumented Dart Impact			ExxonMobil Method
-40°F (-40°C)	1.3 ft-lb	1.8 J	
73°F (23°C)	11 ft-lb	16 J	

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

All physical properties were measured on compression molded specimens.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ LDPE LD 637.LI
Low Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com