

ExxonMobil™ PP4052E1

Polypropylene Homopolymer

Product Description

An easy-processing, high crystallinity, polypropylene homopolymer resin designed primarily for BOPP (biaxially oriented polypropylene) film

General					
Availability ¹	 North America 				
Uses	 Oriented Film 	 Packaging 		 Tape 	
Appearance	 Natural Color 				
Form(s)	 Pellets 				
Processing Method	Film Extrusion				
Revision Date	• 06/01/2016				
Physical	Typical Value (English)	Typical Value	(SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg	g) 2.0 d	g/10 min	2.0	g/10 min	ASTM D1238

Tensile Strength at Yield AS 2.0 in/min (51 mm/min) 5230 psi 36.0 MPa	est Based On STM D638
2.0 in/min (51 mm/min) 5230 psi 36.0 MPa	STM D638
,	
Flongation at Yield (2.0 in/min (51 mm/min)) 8.3 % AS	
210119010110111111111111111111111111111	STM D638
Flexural Modulus - 1% Secant	
0.051 in/min (1.3 mm/min) 248000 psi 1710 MPa AS	STM D790A
0.51 in/min (13 mm/min) 283000 psi 1950 MPa AS	STM D790B
Impact Typical Value (English) Typical Value (SI) Tes	est Based On
Notched Izod Impact (73°F (23°C)) 0.80 ft·lb/in 43 J/m AS	STM D256A
Thermal Typical Value (English) Typical Value (SI) Tes	est Based On
3 · J · · · · · · · · · · · · · · · · ·	xonMobil ethod
Deflection Temperature Under Load (DTUL) 207 °F 97.0 °C AS at 66psi - Unannealed	STM D648

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Notes

Typical properties: these are not to be construed as specifications.

Effective Date: 06/01/2016 ExxonMobil Page: 1 of 2

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ PP4052E1
Polypropylene Homopolymei



For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com