

Santoprene™ 201-80

Thermoplastic Vulcanizate

Product Description

A soft, colorable, versatile thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion, blow molding, thermoforming or vacuum forming. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component.
- Although not NSF certified, this product has a Material Supplier Form on file with NSF to facilitate its evaluation for use in applications requiring NSF certification.
- Recommended for applications requiring excellent flex fatigue resistance.
- Excellent ozone resistance.

General

| | | | |
|---------------------------|--|---|--|
| Availability ¹ | <ul style="list-style-type: none"> • Africa & Middle East • Asia Pacific | <ul style="list-style-type: none"> • Europe • Latin America | <ul style="list-style-type: none"> • North America |
| Applications | <ul style="list-style-type: none"> • Automotive - Plugs, Bumpers, Grommets, Clips • Automotive - Seals and Gaskets | <ul style="list-style-type: none"> • Industrial - Seals and Gaskets • Soft Touch Grips | <ul style="list-style-type: none"> • Tubing |
| Uses | <ul style="list-style-type: none"> • Appliance Components • Automotive Applications • Automotive Under the Hood | <ul style="list-style-type: none"> • Consumer Applications • Diaphragms • Electrical Parts | <ul style="list-style-type: none"> • Gaskets • Seals • Tubing |
| Agency Ratings | <ul style="list-style-type: none"> • UL QMFZ2 | <ul style="list-style-type: none"> • UL QMFZ8 | |
| RoHS Compliance | <ul style="list-style-type: none"> • RoHS Compliant | | |
| Automotive Specifications | <ul style="list-style-type: none"> • CHRYSLER MS-AR-100 DGN | <ul style="list-style-type: none"> • FORD WSD-M2D381-A1 | |
| UL File Number | <ul style="list-style-type: none"> • E80017 | | |
| Color | <ul style="list-style-type: none"> • Natural Color | | |
| Form(s) | <ul style="list-style-type: none"> • Pellets | | |
| Processing Method | <ul style="list-style-type: none"> • Blow Molding • Coextrusion • Extrusion • Extrusion Blow Molding | <ul style="list-style-type: none"> • Injection Blow Molding • Injection Molding • Multi Injection Molding • Profile Extrusion | <ul style="list-style-type: none"> • Sheet Extrusion • Thermoforming • Vacuum Forming |
| Revision Date | <ul style="list-style-type: none"> • 10/08/2014 | | |

Physical

| | Typical Value (English) | Typical Value (SI) | Test Based On |
|----------------------------|-------------------------|-------------------------|---------------|
| Density / Specific Gravity | 0.960 | 0.960 | ASTM D792 |
| Density | 0.960 g/cm ³ | 0.960 g/cm ³ | ISO 1183 |
| Detergent Resistance | f3 | f3 | UL 749 |
| Detergent Resistance | f4 | f4 | UL 2157 |

Hardness

| | Typical Value (English) | Typical Value (SI) | Test Based On |
|------------------------------|-------------------------|--------------------|---------------|
| Shore Hardness | | | ISO 868 |
| Shore A, 15 sec, 73°F (23°C) | 86 | 86 | |

Santoprene™ 201-80
Thermoplastic Vulcanizate

| Elastomers | Typical Value (English) | Typical Value (SI) | Test Based On |
|---|-------------------------|--------------------|---------------|
| Tensile Stress at 100% - Across Flow (73°F (23°C)) | 682 psi | 4.70 MPa | ASTM D412 |
| Tensile Stress at 100% - Across Flow (73°F (23°C)) | 682 psi | 4.70 MPa | ISO 37 |
| Tensile Strength at Break - Across Flow (73°F (23°C)) | 1610 psi | 11.1 MPa | ASTM D412 |
| Tensile Stress at Break - Across Flow (73°F (23°C)) | 1610 psi | 11.1 MPa | ISO 37 |
| Elongation at Break - Across Flow (73°F (23°C)) | 540 % | 540 % | ASTM D412 |
| Tensile Strain at Break - Across Flow (73°F (23°C)) | 540 % | 540 % | ISO 37 |
| Compression Set | | | ASTM D395B |
| 158°F (70°C), 22 hr, Type 1 | 41 % | 41 % | |
| 257°F (125°C), 70 hr, Type 1 | 47 % | 47 % | |
| Compression Set | | | ISO 815 |
| 158°F (70°C), 22 hr, Type A | 41 % | 41 % | |
| 257°F (125°C), 70 hr, Type A | 47 % | 47 % | |
| Thermal | Typical Value (English) | Typical Value (SI) | Test Based On |
| Brittleness Temperature | -76 °F | -60 °C | ASTM D746 |
| Brittleness Temperature | -76 °F | -60 °C | ISO 812 |
| RTI Elec | 212 °F | 100 °C | UL 746 |
| RTI Str | | | UL 746 |
| 0.04 in (1.0 mm) | 194 °F | 90.0 °C | |
| 0.06 in (1.5 mm) | 203 °F | 95.0 °C | |
| 0.12 in (3.0 mm) | 212 °F | 100 °C | |
| Electrical | Typical Value (English) | Typical Value (SI) | Test Based On |
| Dielectric Strength | | | ASTM D149 |
| 73°F (23°C), 0.0787 in (2.00 mm) | 820 V/mil | 32 kV/mm | |
| Dielectric Constant | | | ASTM D150 |
| 73°F (23°C), 0.0780 in (1.98 mm) | 2.30 | 2.30 | |
| Dielectric Constant | | | IEC 60250 |
| 73°F (23°C), 0.0780 in (1.98 mm) | 2.30 | 2.30 | |
| Comparative Tracking Index (CTI) | PLC 0 | PLC 0 | UL 746 |
| High Amp Arc Ignition (HAI) | PLC 0 | PLC 0 | UL 746 |
| High Voltage Arc Resistance to Ignition (HVAR) | PLC 6 | PLC 6 | UL 746 |
| High Voltage Arc Tracking Rate (HVTR) | PLC 1 | PLC 1 | UL 746 |
| Hot-wire Ignition (HWI) | | | UL 746 |
| 0.04 in (1.0 mm) | PLC 4 | PLC 4 | |
| 0.06 in (1.5 mm) | PLC 3 | PLC 3 | |
| 0.12 in (3.0 mm) | PLC 2 | PLC 2 | |

Santoprene™ 201-80
Thermoplastic Vulcanizate

| Injection | Typical Value (English) | Typical Value (SI) |
|-------------------------|---------------------------------|-------------------------|
| Drying Temperature | 180 °F | 82 °C |
| Drying Time | 3.0 hr | 3.0 hr |
| Suggested Max Moisture | 0.080 % | 0.080 % |
| Suggested Max Regrind | 20 % | 20 % |
| Rear Temperature | 350 °F | 177 °C |
| Middle Temperature | 360 °F | 182 °C |
| Front Temperature | 370 °F | 188 °C |
| Nozzle Temperature | 380 to 450 °F | 193 to 232 °C |
| Processing (Melt) Temp | 390 to 450 °F | 199 to 232 °C |
| Mold Temperature | 50 to 125 °F | 10 to 52 °C |
| Injection Rate | Fast | Fast |
| Back Pressure | 50.0 to 100 psi | 0.345 to 0.689 MPa |
| Screw Speed | 100 to 200 rpm | 100 to 200 rpm |
| Clamp Tonnage | 3.0 to 5.0 tons/in ² | 41 to 69 MPa |
| Cushion | 0.125 to 0.250 in | 3.18 to 6.35 mm |
| Screw L/D Ratio | 16.0:1.0 to 20.0:1.0 | 16.0:1.0 to 20.0:1.0 |
| Screw Compression Ratio | 2.0:1.0 to 2.5:1.0 | 2.0:1.0 to 2.5:1.0 |
| Vent Depth | 1.0E-3 in | 0.025 mm |

Injection Notes

Santoprene™ TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Injection Molding Guide.

| Extrusion | Typical Value (English) | Typical Value (SI) |
|--------------------|-------------------------|--------------------|
| Drying Temperature | 180 °F | 82 °C |
| Drying Time | 3.0 hr | 3.0 hr |
| Melt Temperature | 395 °F | 202 °C |
| Die Temperature | 400 °F | 204 °C |
| Back Pressure | 725 to 2900 psi | 5.00 to 20.0 MPa |

Extrusion Notes

Santoprene™ TPV is incompatible with acetal and PVC. For more information regarding processing and die design, please consult our Extrusion Molding Guide.

| Aging | Typical Value (English) | Typical Value (SI) | Test Based On |
|---|-------------------------|--------------------|---------------|
| Change in Tensile Strength in Air 302°F (150°C), 168 hr | -5.0 % | -5.0 % | ASTM D573 |
| Change in Tensile Strength in Air 302°F (150°C), 168 hr | -5.0 % | -5.0 % | ISO 188 |
| Change in Ultimate Elongation in Air 302°F (150°C), 168 hr | -12 % | -12 % | ASTM D573 |
| Change in Tensile Strain at Break in Air 302°F (150°C), 168 hr | -12 % | -12 % | ISO 188 |
| Change in Durometer Hardness in Air Shore A, 302°F (150°C), 168 hr | 5.0 | 5.0 | ASTM D573 |
| Change in Shore Hardness in Air Shore A, 302°F (150°C), 168 hr | 5.0 | 5.0 | ISO 188 |
| Continuous Upper Temperature Resistance 1008 hr | 275 °F | 135 °C | SAE J2236 |

Santoprene™ 201-80

Thermoplastic Vulcanizate

| Flammability | Typical Value (English) | Typical Value (SI) | Test Based On |
|------------------|-------------------------|--------------------|---------------|
| Flame Rating | | | UL 94 |
| 0.04 in (1.0 mm) | HB | HB | |
| 0.06 in (1.5 mm) | HB | HB | |
| 0.12 in (3.0 mm) | HB | HB | |

Additional Information

Where applicable, test results based on fan gated, injection molded plaques.

Tensile strength, elongation and tensile stress are measured across the flow direction - ISO type 1, ASTM die C.

Compression set at 25% deflection.

All products purchased directly from an ExxonMobil affiliate in Europe are REACH compliant. For products not imported into Europe by ExxonMobil, customers should assess their legal responsibilities under REACH.

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For detailed Product Stewardship information, please contact Customer Service.

Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene™ TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. For more information, please consult our Safety Data Sheet, Injection Molding Guide and Extrusion Guide.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2018 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.