

Exact™ 5101

Ethylene-based Plastomer Resin

Product Description

Exact™ 5101 plastomer resin is an ethylene 1-octene copolymer produced using a proprietary metallocene Technology. Exact™ 5101 is designed for use in both monolayer and multilayer blown film applications requiring outstanding sealing performance and toughness.

Key Features

- Excellent low temperature sealability
- Outstanding toughness and impact strength
- High clarity
- Low hexane extractables
- Low modulus

General

Availability ¹	<ul style="list-style-type: none"> ▪ Africa & Middle East ▪ Asia Pacific 	<ul style="list-style-type: none"> ▪ Europe ▪ North America
Applications	<ul style="list-style-type: none"> ▪ Blown Film ▪ Food Packaging 	<ul style="list-style-type: none"> ▪ Laminated films ▪ Multilayer Packaging Film ▪ Stretch Hood
Form(s)	<ul style="list-style-type: none"> ▪ Pellets 	
Revision Date	<ul style="list-style-type: none"> ▪ 12/08/2022 	

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.900 g/cm ³	0.900 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	1.1 g/10 min	1.1 g/10 min	ASTM D1238

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	170 °F	76.6 °C	ExxonMobil Method
Peak Melting Temperature	198 °F	92 °C	ExxonMobil Method

Films	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	660 psi	4.6 MPa	ASTM D882
Tensile Strength at Yield TD	510 psi	3.5 MPa	ASTM D882
Tensile Strength at Break MD	11000 psi	70 MPa	ASTM D882
Tensile Strength at Break TD	9800 psi	70 MPa	ASTM D882
Elongation at Break MD	440 %	440 %	ASTM D882
Elongation at Break TD	660 %	660 %	ASTM D882
Secant Modulus MD - 1% Secant	7300 psi	50 MPa	ASTM D882
Secant Modulus TD - 1% Secant	8100 psi	56 MPa	ASTM D882
Dart Drop Impact	590 g	590 g	ASTM D1709A
Elmendorf Tear Strength MD	70 g	70 g	ASTM D1922
Elmendorf Tear Strength TD	270 g	270 g	ASTM D1922
Puncture Force	14 lbf	62 N	ExxonMobil Method
Puncture Energy	53 in-lb	6.0 J	ExxonMobil Method

Optical	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	81	81	ASTM D2457
Haze	2.4 %	2.4 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (1.0mil/25.4 micron) made from Exact 5101 resin on a 2.6 inch (65 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 400°F (204°C), a 60 mil (1.52 mm) die gap at a rate of 10 lbs/hr/in die circumference(1.79 kg/hr/cm).

Exact™ 5101
Ethylene-based Plastomer Resin

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com